



Valued Quality. Delivered.

Hong Kong Government Recognized Service Supplier
Approved Laboratory of The Woolmark Company

Members of :

American National Standards Institute Hong Kong Association for Testing, Inspection and Certification Limited
American Society for Testing and Materials Hong Kong Toys Council
British Standards Institute

Number: H KGT03896794

TEST REPORT

Applicant: D & D ZIPPER TRADING LTD
RM 2302 CHEUNG TAT CENTRE
18 CHEUNG LEE ST
CHAI WAN
HONG KONG

Date: May 14, 2014

Attn: BILLY CHAN

Sample Description As Declared :

No. Of Sample : One
Fibre Content : -
Material : DND No.5 Nylon Coil Zipper Close End With A/L DR304 Pull (Clear Plastic Top & End Top)
Finishing : -
End Uses : Women's Knitwear
Colour : Black
Style No. : OLAW14
Order No./PO No. : -
Standard : Cotton Trader Standard
Buyer's Name : Cotton Trader
Manufacturer's Name : Derlin Zipper Fty
Ref. : Agent: Caretex Apparel SDN BHD

Applicant's Provided Care Instruction/Label :

-

Date Received/Date Test Started : May 09, 2014

Conclusion:

Zipper Strength M

Note : M = Meet Buyer's Requirement F = Below Buyer's Requirement
= No Comment N/A = Not Applicable
C = Conform Label - = Did Not Perform
* = See Remark

For and on behalf of
Intertek Testing Services Hong Kong Limited

Jason Y.M. Ho
Vice President



Valued Quality. Delivered.

Hong Kong Government Recognized Service Supplier
Approved Laboratory of The Woolmark Company

Members of :

American National Standards Institute Hong Kong Association for Testing, Inspection and Certification Limited
American Society for Testing and Materials Hong Kong Toys Council
British Standards Institute

Number: HKGT03896794

TEST REPORT

Tests Conducted (As Requested By The Applicant)

1 Zipper Strength (BS 3084-2006):

		<u>Requirement</u>
Size And Designation :	Medium Type Closed-End Fastener	
(I) Strength of Puller Attachment	235.7 N (Connector deformed & Puller detached)	200 N min
(II) Strength of Closed-End	167.5 N	80 N min
(III) Strength of Top-Stop	183.6 N	90 N min
(IV) Resistance to Reciprocation	Over 500 cycles	500 Cycles
(V) Lateral Strength of Fastener	1041.3 N (Stitching breakdown)	250 N min
(VI) Strength of Slider Locking Device	128.4 N	25 N min

Remark : N = Newton

End of Report

This report is made solely on the basis of your instructions and/or information and materials supplied by you. It is not intended to be a recommendation for any particular course of action. Intertek does not accept a duty of care or any other responsibility to any person other than the Client in respect of this report and only accepts liability to the Client insofar as is expressly contained in the terms and conditions governing Intertek's provision of services to you. Intertek makes no warranties or representations either express or implied with respect to this report save as provided for in those terms and conditions. We have aimed to conduct the Review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute or otherwise, except in the event of our gross negligence or wilful misconduct.